



<b>Title of Change:</b>	Gold wire to bare copper wire conversion for Diode devices assembled in ON Semiconductor Leshan facility.	
<b>Proposed Changed Material First Ship Date:</b>	18 March 2020	
<b>Current Material Last Order Date:</b>	11 September 2019 Orders received after the Current Material Last Order Date expiration are to be considered as orders for new changed material as described in this PCN. Orders for current (unchanged) material after this date will be per mutual agreement and current material inventory availability.	
<b>Current Material Last Delivery Date:</b>	11 December 2019 The Current Material Last Delivery Date may be subject to change based on build and depletion of the current (unchanged) material inventory.	
<b>Product Category:</b>	Active components – Discrete components	
<b>Contact information:</b>	Contact your local ON Semiconductor Sales Office or <Andy.Tao@onsemi.com>	
<b>Samples:</b>	Contact your local ON Semiconductor Sales Office to place sample order or <PCN.samples@onsemi.com> Sample requests are to be submitted no later than 45 days after publication of this change notification.	
<b>Sample Availability Date:</b>	26 April 2019	
<b>PPAP Availability Date:</b>	26 April 2019	
<b>Additional Reliability Data:</b>	Contact your local ON Semiconductor Sales Office or <Rui.Zhang@onsemi.com>	
<b>Type of Notification:</b>	This is a Final Product/Process Change Notification (FPCN) sent to customers. FPCNs are issued 12 months prior to implementation of the change or earlier upon customer approval. ON Semiconductor will consider this proposed change and it's conditions acceptable, unless an inquiry is made in writing within 45 days of delivery of this notice. To do so, contact PCN.Support@onsemi.com.	
<b>Change Category</b>	<b>Type of Change</b>	
Process – Assembly	Change of wire bonding	
<b>Description and Purpose:</b>		
Upon the expiration of this PCN, these devices will be built with 0.8mils bare copper wire at the same site. Datasheet specifications and product electrical performance remain unchanged. Reliability qualification and full electrical characterization over temperature has been performed.		
	<b>Before Change Description</b>	<b>After Change Description</b>
Bond Wire	0.8 mils gold wire	0.8 mils bare copper wire
<b>Reason / Motivation for Change:</b>	<b>Change benefits for customer:</b> Copper wire is with higher Thermal conductivity and lower resistivity. <b>Risk for late release for customer:</b> Longer lead time due to limited flexibility in terms of manufacturing and capacity planning.	
<b>Anticipated impact on fit, form, function, reliability, product safety or manufacturability</b>	The device has been qualified and validated based on the same Product Specification. The device has successfully passed the qualification tests. Potential impacts can be identified, but due to testing performed by ON Semiconductor in relation to the PCN, associated risks are verified and excluded.  No anticipated impacts.	
<b>Sites Affected:</b>	ON Semiconductor Sites: ON Leshan, China	External Foundry/Subcon Sites: None



<b>Marking of Parts/ Traceability of Change:</b>	Products assembled with 0.8mils bare copper wire from ON Semiconductor Leshan facility will have a Finish Goods Date Code of WW11, 2020 or later.
--	---

**Reliability Data Summary:**

**QV DEVICE NAME: SBAS16XV2T1G**

**PACKAGE: SOD523**

Test	Specification	Condition	Interval	Results
HTRB	JESD22-A108	Ta=150°C, 100% max rated V	1008 hrs	0/231
HTSL	JESD22-A103	Ta= 150°C	2016 hrs	0/231
IOL	MIL-STD-750 (M1037) AEC-Q101	Ta=+25°C, delta Tj=100°C On/off = 2 min	30K cyc	0/231
TC	JESD22-A104	Ta= -65°C to +150°C	2000 cyc	0/231
HAST	JESD22-A110	130°C, 85% RH, 18.8psig, 80% rated V, or 100V max	192 hrs	0/231
AC	JESD22-A102	121°C, 100% RH, 15psig, unbiased	96 hrs	0/231
PC	J-STD-020 JESD-A113	MSL 1 @ 260 °C	-	0/924
RSH	JESD22- B106	Ta = 265°C, 10 sec	-	0/30
SD	JSTD002	Ta = 245°C, 10 sec	-	0/30

**QV DEVICE NAME: SVMBD770DW1T1G**

**PACKAGE: SC88**

Test	Specification	Condition	Interval	Results
HTRB	JESD22-A108	Ta=150°C, 100% max rated V	1008 hrs	0/231
HTSL	JESD22-A103	Ta= 150°C	2016 hrs	0/231
IOL	MIL-STD-750 (M1037) AEC-Q101	Ta=+25°C, delta Tj=100°C On/off = 2 min	30K cyc	0/231
TC	JESD22-A104	Ta= -65°C to +150°C	2000 cyc	0/231
HAST	JESD22-A110	130°C, 85% RH, 18.8psig, 80% rated V, or 100V max	192 hrs	0/231
AC	JESD22-A102	121°C, 100% RH, 15psig, unbiased	96 hrs	0/231
PC	J-STD-020 JESD-A113	MSL 1 @ 260 °C	-	0/924
RSH	JESD22- B106	Ta = 265°C, 10 sec	-	0/30
SD	JSTD002	Ta = 245°C, 10 sec	-	0/30

**Note: AEC-1pager is attached.**

To access file attachments on pdf copy of PCN, please be guided by the steps below:

1. Download pdf copy of the PCN to your computer
2. Open the downloaded pdf copy of the PCN
3. Click on the paper clip icon available on the menu provided in the left/bottom portion of the screen to reveal the Attachment field
4. Then click on the attached file/s

**Electrical Characteristic Summary:**

The temperature characterization and ESD performance meet datasheet specification. Detail of electrical characterization result is available upon request.

Electrical characteristics are not impacted.

**List of Affected Parts:**

**Note:** Only the standard (off the shelf) part numbers are listed in the parts list. Any custom parts affected by this PCN are shown in the customer specific PCN addendum in the PCN email notification, or on the [PCN Customized Portal](#).

Current Part Number	New Part Number	Qualification Vehicle
SM1MA142WAT1G	NA	NSVMBD770DW1T1G
SM1MA142WKT1G	NA	NSVMBD770DW1T1G
NSVBAS16WT3G	NA	NSVMBD770DW1T1G
SBAS16WT1G	NA	NSVMBD770DW1T1G
NSV1SS400T1G	NA	SBAS16XV2T1G
SBAS16XV2T1G	NA	SBAS16XV2T1G
NSVBAT54WT1G	NA	NSVMBD770DW1T1G
SMMBD330T1G	NA	NSVMBD770DW1T1G
SMMBD770T1G	NA	NSVMBD770DW1T1G
NSVBAT54SWT1G	NA	NSVMBD770DW1T1G
SBAT54CWT1G	NA	NSVMBD770DW1T1G
NSVMBD770DW1T1G	NA	NSVMBD770DW1T1G
NSVRB751S40T1G	NA	SBAS16XV2T1G
NSV1SS400T5G	NA	SBAS16XV2T1G
NSVRB751S40T5G	NA	SBAS16XV2T1G
SBAS16XV2T5G	NA	SBAS16XV2T1G

Japanese translation of the notification starts here.  
通知の日本語訳はここから始まります。

*Note: The Japanese version is for reference only. In case of any differences between the English and Japanese version, the English version shall control.*

注：日本語版は参照用です。英語版と日本語版の違いがある場合は、英語版が優先されます。



変更件名:	オン・セミコンダクター楽山工場で組み立てられるびダイオード製品における金ワイヤーから銅ワイヤーへの変更							
初回出荷予定日:	18 March 2020							
現在の材料の最終注文日:	11 September 2019 既存品の最終注文日以降の注文は、この PCN に記載されている変更後品の注文とみなされます。この日付より後の既存品(変更前品)の注文は、相互契約により変更前品の在庫状況に応じて履行されます。							
現在の材料の最終出荷日:	11 December 2019 既存品(変更前品)の最終出荷日は、変更前品の製造および在庫の状況によって変更されることがあります。							
製品カテゴリ:	アクティブなコンポーネント - 個別コンポーネント							
連絡先情報:	現地のオン・セミコンダクター営業所または <Andy.Tao@onsemi.com> お問い合わせください。							
サンプル:	現地のオン・セミコンダクター営業所に注文するか、または <PCN.samples@onsemi.com> お問い合わせください。サンプルは、この変更通知の発行から 45 日以内に要求してください。							
サンプル提供開始可能日:	26 April 2019							
PPAP 提供開始日:	26 April 2019							
追加の信頼性データ:	お客さまの地域のオン・セミコンダクター営業所または <Rui.Zhang@onsemi.com> お問い合わせください。							
通知種別:	これは、お客様宛の最終製品 / プロセス変更通知 (FPCN) です。 FPCN は、変更実施の 12 か月前、またはお客様からの承認が得られた場合はそれ以前に発行されることがあります。 オン・セミコンダクターは、この通知の送付から 45 日以内に書面による問い合わせが行われないうちに、この変更希望およびその条件が受諾されたものとみなします。お問い合わせは、PCN.Support@onsemi.com お願いします。							
変更カテゴリ:	変更種別							
プロセス - 組み立て	ワイヤボンディングの変更							
説明および目的:	<p>本PCNの実施により、対象製品は同拠点で0.8mils 銅ワイヤーを使って生産されるようになります。データシート規格および製品の電気的特性に変更はありません。信頼性認定試験と電気特性温度評価は実施されています。</p> <table border="1"> <thead> <tr> <th></th> <th>変更前の表記</th> <th>変更後の表記</th> </tr> </thead> <tbody> <tr> <td>ボンドワイヤー</td> <td>0.8 mils gold wire</td> <td>0.8 mils bare copper wire</td> </tr> </tbody> </table>			変更前の表記	変更後の表記	ボンドワイヤー	0.8 mils gold wire	0.8 mils bare copper wire
	変更前の表記	変更後の表記						
ボンドワイヤー	0.8 mils gold wire	0.8 mils bare copper wire						
変更の理由 / 動機:	<p><b>変更に伴うお客様のメリット:</b> 銅ワイヤーは高い熱伝導率と低い抵抗を有します。 <b>お客様への実施遅延のリスク:</b> 製造および生産計画についての柔軟性が制限されるため、リードタイムが長くなります。</p>							
適合性、形状、機能、信頼性、製品安全性、または製造可能性に関して見込まれる影響	<p>対象製品は同じ製品仕様に基づいて認定および検証されています。製品は認定試験に正常に合格しています。潜在的な影響が確認される可能性があります。オン・セミコンダクターが PCN に関して実施する検査により、関連するリスクは検証および排除されます。</p> <p>予想される影響はありません。</p>							
影響を受ける拠点:	オン・セミコンダクター拠点: ON Leshan, China	外部製造工場 / 下請業者拠点: なし						



部品の表示 / 変更の追跡可能性:

オン・セミコンダクター 楽山工場 で組み立てられた 0.8 mils 銅ワイヤー品の日付コードは WW11, 2020 以降になりません。

信頼性データの要約:

デバイス名: SBAS16XV2T1G

パッケージ: SOD523

テスト	仕様	条件	間隔	結果
HTRB	JESD22-A108	Ta=150°C, 100% max rated V	1008 hrs	0/231
HTSL	JESD22-A103	Ta= 150°C	2016 hrs	0/231
IOL	MIL-STD-750 (M1037) AEC-Q101	Ta=+25°C, delta Tj=100°C On/off = 2 min	30K cyc	0/231
TC	JESD22-A104	Ta= -65°C to +150°C	2000 cyc	0/231
HAST	JESD22-A110	130°C, 85% RH, 18.8psig, 80% rated V, or 100V max	192 hrs	0/231
AC	JESD22-A102	121°C, 100% RH, 15psig, unbiased	96 hrs	0/231
PC	J-STD-020 JESD-A113	MSL 1 @ 260 °C	-	0/924
RSH	JESD22- B106	Ta = 265°C, 10 sec	-	0/30
SD	JSTD002	Ta = 245°C, 10 sec	-	0/30

デバイス名 NSVMBD770DW1T1G

パッケージ: SC88

テスト	仕様	条件	間隔	結果
HTRB	JESD22-A108	Ta=150°C, 100% max rated V	1008 hrs	0/231
HTSL	JESD22-A103	Ta= 150°C	2016 hrs	0/231
IOL	MIL-STD-750 (M1037) AEC-Q101	Ta=+25°C, delta Tj=100°C On/off = 2 min	30K cyc	0/231
TC	JESD22-A104	Ta= -65°C to +150°C	2000 cyc	0/231
HAST	JESD22-A110	130°C, 85% RH, 18.8psig, 80% rated V, or 100V max	192 hrs	0/231
AC	JESD22-A102	121°C, 100% RH, 15psig, unbiased	96 hrs	0/231
PC	J-STD-020 JESD-A113	MSL 1 @ 260 °C	-	0/924
RSH	JESD22- B106	Ta = 265°C, 10 sec	-	0/30
SD	JSTD002	Ta = 245°C, 10 sec	-	0/30

注: AEC 1 ページャーを添付しています。

添付文書を見るには:

1. ご使用のコンピューターに PDF 版の PCN をダウンロードします。
2. ダウンロードした PDF 版の PCN を開きます。
3. 添付欄を見るには、画面左 / 下部分のメニュー上にあるクリップ アイコンをクリックしてください。
4. 添付ファイルをクリックします

**電気的特性の要約:**

温度特性と ESD 性能はデータシートの規格を満たしています。電気的特性評価結果の詳細はご要望により提供可能です。

電気的特性への影響はありません。

**影響を受ける部品の一覧:**

注: 標準の部品番号(既製品)のみが部品一覧に記載されます。本 PCN に影響を受けるカスタム 部品は、PCN メールのお客様の特定の PCN の付属文書、または PCN カスタマイズポータルに記載されています。

現在の部品番号	新部品番号	認定試験用ピークル
SM1MA142WAT1G	NA	NSVMBD770DW1T1G
SM1MA142WKT1G	NA	NSVMBD770DW1T1G
NSVBAS16WT3G	NA	NSVMBD770DW1T1G
SBAS16WT1G	NA	NSVMBD770DW1T1G
NSV1SS400T1G	NA	SBAS16XV2T1G
SBAS16XV2T1G	NA	SBAS16XV2T1G
NSVBAT54WT1G	NA	NSVMBD770DW1T1G
SMMBD330T1G	NA	NSVMBD770DW1T1G
SMMBD770T1G	NA	NSVMBD770DW1T1G
NSVBAT54SWT1G	NA	NSVMBD770DW1T1G
SBAT54CWT1G	NA	NSVMBD770DW1T1G
NSVMBD770DW1T1G	NA	NSVMBD770DW1T1G
NSVRB751S40T1G	NA	SBAS16XV2T1G
NSV1SS400T5G	NA	SBAS16XV2T1G
NSVRB751S40T5G	NA	SBAS16XV2T1G
SBAS16XV2T5G	NA	SBAS16XV2T1G



**Appendix A: Changed Products**

D

Product	Customer Part Number	New Part Number	Qualification Vehicle
NSV1SS400T1G		NA	SBAS16XV2T1G
NSVBAS16WT3G		NA	NSVMBD770DW1T1G
NSVBAT54SWT1G		NA	NSVMBD770DW1T1G
NSVBAT54WT1G		NA	NSVMBD770DW1T1G
NSVMBD770DW1T1G		NA	NSVMBD770DW1T1G
NSVRB751S40T1G		NA	SBAS16XV2T1G
SBAS16WT1G		NA	NSVMBD770DW1T1G
SBAS16XV2T1G		NA	SBAS16XV2T1G
SBAT54CWT1G		NA	NSVMBD770DW1T1G
SM1MA142WAT1G		NA	NSVMBD770DW1T1G
SM1MA142WKT1G		NA	NSVMBD770DW1T1G
SMMBD330T1G		NA	NSVMBD770DW1T1G
SMMBD770T1G		NA	NSVMBD770DW1T1G